

Characteristics and features

- EPDM quality
- sulfur cured
- insulating blanket
- VDE certificated according DIN EN 61112 cat. A, Z
- ozone and sulfur acid resistant
- PAH content according AfPS GS 2014: category 1

Physical data

Polymer		DIN ISO 1629	EPDM
Colour			salmon pink (RAL 3022)
Hardness	Shore A	ISO 48-4	60 ± 5
Density	g/cm³	DIN EN ISO 1183 / ISO 2781	1,18 ± 0,02
Tensile strength	MPa	ISO 37	> 12
Elongation at break	%	ISO 37	> 300
Temperature resistance	°C		-50°C to +100°C
Tear resistance	N/mm	DIN ISO 34-1A	> 7,0
Compression set*	%	ISO 815	< 35
Fire resistance**		FMVSS 302	B (hardly inflammable)
Ozone resistance ***		ISO 1431-1	ozone resistant
Spec. Volume resistance	Ωcm	VDE 0303-30	isolating

* 24 h / 70 °C; ** tested at bei 2 mm; *** 50 pphm, 40°C, 72 h, 20% Elongation

With the publication of this technical data sheet, all previously published data sheets lose their validity.

Important information:

The above data is based on accompanying compound release tests and represents product classification numbers, however they do not contain ascertained properties and cannot be binding. We reserve the right to alter product constants with the scope of technical progress or new developments. This document was printed by computer therefore not signed.

Status from 01.12.2023/ Revision 3

Index 03

Holcim Technical Solutions and Products GmbH Sitz der Gesellschaft Edingen-Neckarhausen Eintragung Amtsgericht Mannheim HRB 337880 Geschäftsführung: Emilien Collard, Robert Forster

Steuer-Nr.: 37009/50500 UID-Nr.: DE 813571753

Postanschrift Fred-Joachim-Schoeps-Str. 55 D-68535 Edingen-Neckarhausen Telefon: 0621/480-280-0 Fax: 0621/480-280-240 Postfachanschrift Postfach 710262 D-68222 Friedrichsfeld

A-KX 55-15

PAH-free



The listed test values and data are based on results of many years of development, tests and proving. A characteristics warranty and guaranteed function can't be derived from the information given. It is within the user's responsibility to test the selection of material in a specific application to ascertain his intended operational capability. Technical changes within the product development are subject to change.