

## **Characteristics and features**

- NBR quality
- peroxide cured
- ACN content > 33%
- resistant against hydraulic oil
- resistant against biogas and biodiesel
- applicable up to 120°C for a short time

# PAH-free EU 1272/2013 REACHconform Nitrosamine -free

RoHS 2conform

## **Physical data**

| Polymer                 |                   | DIN ISO 1629          | NBR                    |
|-------------------------|-------------------|-----------------------|------------------------|
| i olymei                |                   |                       |                        |
| Colour                  |                   |                       | black                  |
|                         |                   |                       |                        |
| Hardness                | Shore A           | ISO 48-4              | 62 ± 5                 |
| Density                 | g/cm <sup>3</sup> | DIN EN ISO 1183 / ISO | 1,30 ± 0,02            |
|                         | <b>J</b>          | 2781                  | ) = ) =                |
| Tensile strength        | MPa               | ISO 37                | >7                     |
|                         |                   |                       |                        |
| Elongation at break     | %                 | ISO 37                | > 500                  |
| Temperature resistance  | °C                |                       | -25°C to +120°C        |
|                         | 0                 |                       |                        |
| Tear resistance         | N/mm              | DIN ISO 34-1A         | > 7,0                  |
|                         |                   |                       |                        |
| Compression set*        | %                 | ISO 815               | < 35                   |
|                         |                   |                       |                        |
| Fire resistance**       |                   | FMVSS 302             | B (hardly inflammable) |
| Ozon resistance***      |                   | ISO 1431-1            | not ozone resistant    |
|                         |                   |                       |                        |
| Spec. Volume resistance | Ωcm               | VDE 0303-30           | isolating              |
|                         |                   |                       |                        |

\* 24 h / 70 °C; \*\* tested at 2 mm; \*\*\* 50 pphm, 40°C, 72 h, 20% Elongation

## With the publication of this technical data sheet, all previously published data sheets lose their validity.

#### Important information:

The above data is based on accompanying compound release tests and represents product classification numbers, however they do not contain ascertained properties and cannot be binding. We reserve the right to alter product constants with the scope of technical progress or new developments. This document was printed by computer therefore not signed.

### Status from 06.12.2023/ issue 2 Index 02

Holcim Technical Solutions and Products GmbH Sitz der Gesellschaft Edingen-Neckarhausen Eintragung Amtsgericht Mannheim HRB 337880 Geschäftsführung: Emilien Collard, Robert Forster Steuer-Nr.: 37009/50500 UID-Nr.: DE 813571753 Postanschrift Fred-Joachim-Schoeps-Str. 55 D-68535 Edingen-Neckarhausen Telefon: 0621/480-280-0 Fax: 0621/480-280-240 Postfachanschrift Postfach 710262 D-68222 Friedrichsfeld

# A-NJ 62-89

The listed test values and data are based on results of many years of development, tests and proving. A characteristics warranty and guaranteed function can't be derived from the information given. It is within the user's responsibility to test the selection of material in a specific application to ascertain his intended operational capability. Technical changes within the product development are subject to change.